

EXTERNAL EXPOSURE TO FIRE CLASSIFICATION REPORT OF ROOF COVERING

Sponsor: LLC Zavod LOGICROOF
Vostochnij Promuzel, 21
391000 Ryazan, Russian Federation

Prepared by: VTT Expert Services Ltd
Kivimiehentie 4, Espoo
P.O. Box 1001
FI-02044 VTT, Finland

Notified body No: 0809

Product: LOGICROOF V-RP + TechnoNICOL

Classification report No: VTT-S-6889-13



1 Introduction

This classification report defines the classification assigned to the product LOGICROOF V-RP + TechnoNICOL roof covering in accordance with the procedures given in EN 13501-5:2005 + A1:2009.

2 Description of the roof covering

The product LOGICROOF V-RP + TechnoNICOL is described below.

Type of product: roof covering materials

Product descriptions:

LOGICROOF V-RP:

Materials: PVC-P based membrane reinforced with polyester grid

Thickness: 1,2 mm

Mass per unit area: 1,44 kg/m²

TechnoNICOL (separating layer):

Material: fibreglass matt

Mass per unit area: 100 g/m²

3 Test reports and test results in support of classification

3.1 Test report

Name of laboratory	Name of sponsor	Test report	Test method
VTT Expert Services Ltd	LLC Zavod LOGIROOF	VTT-S-6888-13	CEN TS 1187 Test 2

3.2 Test 2

Test pitch: 30°

Substrate: expanded polystyrene, (EPS) (not fire retardant treated), nominal density 20 kg/m³, thickness 50 mm

Parameter	Criteria							Compliance
	Mean	Max	Spe. 1	Spe. 2	Spe. 3	Mean	Max	
Damaged length at 2 m/s – roof covering	≤ 550	≤ 800	454	389	418	420	454	Yes
Damaged length at 2 m/s – substrate	≤ 550	≤ 800	471	420	439	443	471	Yes
Damaged length at 4 m/s – roof covering	≤ 550	≤ 800	408	453	379	413	453	Yes
Damaged length at 4 m/s – substrate	≤ 550	≤ 800	452	448	410	437	452	Yes



The test results relate only to the sample tested.

4 Classification and field of application

4.1 Reference of classification

This classification has been carried out in accordance with EN 13501-5:2005 + A1:2009.

4.2 Classification

The product LOGICROOF V-RP + TechnoNICOL in relation to its external fire performance is classified:

B_{ROOF} (t2)

4.3 Field of application

This classification is valid for the following conditions:

- combustible or non-combustible substrates with density of at least 15 kg/m³

5 Limitations

This classification report does not represent type approval or certification of the products.

Espoo, 4 October 2013



Kai Renholm
Business Manager



Tiia Rynänen
Product Manager

DISTRIBUTION Customer
Archive

Original (2)
Original



The test results relate only to the sample tested.